

ORACAL® 631 Exhibition Cal

Description

Soft PVC film that features residue-free removal for two years and a matte surface that suppresses unwanted reflection.

Release Paper

78 # custom silicone-coated paper with special release characteristics that provide excellent weeding and release values. Customized blue silicone paper liner for white provides superior contrast for cutting and weeding.

Adhesive

Polyacrylate dispersion, removable

Applications

Due to its special release characteristics, it is ideal for use in die-cut and computer-cut systems. For short and medium-term outdoor applications in displays and exhibition stands. Certified according to DIN 4102-B1.

Technical Data:

Thickness (without protective paper and adhesive)	3 mil
Dimensional Stability (FINAT - TM 14)	adhered to steel, no shrinkage in cross direction; in length, < .016"
Seawaterability (DIN 50 021)	adhered to aluminum, no variation after 48 h/ 73 °F
Temperature Resistance	adhered to aluminum, -40 °F to +176 °F no variation
Adhesive Power (FINAT TM-1, after 24 h, stainless steel, average)	1.65 lb/in
Tensile Strength (DIN EN ISO 527) Along Across	min. 19 MPa min. 19 MPa
Elongation at break (DIN EN ISO 527) Along Across	min. 130% min. 150%
Shelf life (68°F/50% relative humidity)	2 years
Minimum Application Temperature	+50 °F
Available Lengths Available Widths	10 and 50 yard rolls 15 punched, 24, 30 punched, 48
Minimum Life expectancy based on accepted application procedures	3 years

Attention:

Surfaces to which the material will be applied must be cleaned thoroughly of dust, grease or any contaminants. Freshly lacquered or painted surfaces should be allowed to stand for at least three weeks after complete curing. The compatibility of selected lacquers and paints should be tested by the end-user prior to use.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications, customers should independently determine the suitability of this material for their specific purpose, prior to use.



ORACAL USA
A DIVISION OF LIG INTERNATIONAL, INC.
7251 Salisbury Road
Jacksonville, FL 32256 USA
Toll Free 888.672.2251
904.726.9597 • FAX 904.726.9409
www.oracal.com • Oracal USA © 2003