

ORAJET[®] 3951 Professional Wrapping Film

With CommandForm[™] Technology

Description

2.0 mil cast PVC film available in white and transparent gloss

Release Paper

80# PE-coated silicone paper

Adhesive

Grey, repositionable solvent-based permanent adhesive. Removable with applications of heat with no residue.

Areas of Use

Designed specifically to conform to irregular surfaces such as vehicle wraps and other fleet applications

Technical Data:

Thickness (without adhesive and release liner)	2.0 mil
---	---------

Dimensional Stability (FINAT – TM 14)	adhered to steel, no shrinkage in cross direction; in length, < 0.009"
--	---

Seawaterability (DIN 50 021)	adhered to aluminum, after 100 h/ 73°F no variation
-------------------------------------	--

Temperature Resistance	adhered to aluminum, -58°F to +230°F, no variation
-------------------------------	--

Fire Behavior (DIN 75200)	adhered to steel, self-extinguishing
----------------------------------	--------------------------------------

Adhesive Power (FINAT TM-1, after 24 h, stainless steel)	min. 4.1 lb/in
--	----------------

Tensile Strength (DIN EN ISO 527)	
Along	min. 19 MPa / 2755 psi
Across	min. 19 MPa / 2755 psi

Elongation at break (DIN EN ISO 527)	
Along	min. 120%
Across	min. 120%

Shelf life (68°F and 50% relative humidity)	2 years
--	---------

Minimum Application Temperature	> +46°F
--	---------

Available Lengths	164' (50 meters)
Available Widths	12", 16", 30" 36", 54", 54" reverse wound, 60"

Minimum Life by Application Specialist under vertical outdoor exposure	10 years
--	----------

Attention:

Surfaces to which the material will be applied must be cleaned thoroughly of dust, grease or any contaminants. Freshly lacquered or painted surfaces should be allowed to stand for at least three weeks after complete curing. The compatibility of selected lacquers and paints should be tested by the end-user prior to use.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications, customers should independently determine the suitability of this material for their specific purpose, prior to use.

DISTRIBUTED BY: J WALKER SIGN SUPPLY 1-800-248-8872



ORACAL USA
A DIVISION OF LIG INTERNATIONAL, INC.
7251 Salisbury Road
Jacksonville, FL 32256 USA
Toll Free 888.672.2251
904.726.9597 • FAX 904.726.9409
www.oracal.com • Oracal USA © 2003

ORAJET® 3651 Recommended Printers

Solvent-based Printers:

Oce: Arizona 30/90/180/500

Mutoh: Albatros, Toucan

Mimaki: JV3

Nur: Fresco, Salsa, Blueboard

Scitex: Idanit Novo, Grandjet, Press Jet

Vutek: Press Vu, Ultra Vu 3000/3300, Ultra Vu 5000/5300, Ultra Vu 2360 SC, Ultra Vu 3360 SC

Encad: VinylJet 36

DGI: VT-11 62, VT-11 92, VT-100D

Gerber: Orion, Tomahawk

Electrostatic Printers:

Rastergraphics Digital Color

Rastergraphics Station DCS 542

3M Scotchprint

3M 9512 / 2000

Xerox 8954

Thermotransfer Printers:

Summa Technology Dura Chrome

Matan Sprinter

Gerber Edge

Gerber Maxx

Roland PC 60

Roland PC 600

DISTRIBUTED BY: J WALKER SIGN SUPPLY 1-800-248-8872



ORACAL USA

A DIVISION OF LIG INTERNATIONAL, INC.

7251 Salisbury Road

Jacksonville, FL 32256 USA

Toll Free 888.672.2251

904.726.9597 • FAX 904.726.9409

www.oracal.com • Oracal USA © 2003